

# B – H CURVE

**PRESENTED BY:  
Dr. Vivek Ambalkar  
H.O.D PHYSICS  
D. P. VIPRA COLEGE**

# INTRODUCTION

---


- The plot of Magnetization  $M$  or Magnetic field  $B$  as a function of Magnetic Field Intensity  $H$  (i.e.  $M$ - $H$  or  $B$ - $H$  graph) gives the Hysteresis curve. The permeability  $\mu$  of a ferromagnetic material can vary through the entire range of possible values from zero to infinity and may be either positive or negative.

# Hysteresis

---

- Hysteresis, in general, is defined as the lag in a variable property of a system with respect to the effect producing it as this effect varies. In ferromagnetic materials the magnetic flux density  $B$  lags behind the changing external Magnetizing field Intensity  $H$ . Hysteresis curve is drawn by plotting the graph of  $B$ -field vs  $H$  (or  $M$ - $H$ ) by taking the material through a complete cycle of  $H$  values as follows

# Fig. Typical B-H graph (Hysteresis curve) of a ferromagnetic material



# EXPLANATION

---

- First, consider an unmagnetized sample of ferromagnetic material. The magnetic field intensity  $H$  is initially zero at  $O$ .  $H$  is increased monotonically, then magnetic induction  $B$  increases nonlinearly along the curve (OACDE) called as the magnetization curve. At point  $E$  almost all of the magnetic domains are aligned parallel with the magnetic field.


# EXPLANATION

---

- An additional increase in  $H$  does not produce any increase in  $B$ .  $E$  is called as the point of magnetic saturation of the material. Values of permeability derived from the formula along the curve are always positive and show a wide range of values. The maximum permeability as large as occurs at the "knee" (point  $D$ ) of the curve

# EXPLANATION

- Next  $H$  is decreased till it reduces to zero.  $B$  reduces from its saturation value at "E" to that at point "F". Some of the magnetic domains lose their alignment but some maintain alignment i.e. Some magnetic flux density  $B$  is still retained in the material





# EXPLANATION

---

- The curve for decreasing values of  $H$  (i.e. Demagnetization curve  $EF$ ) is offset by an amount  $FO$  from that for increasing values of  $H$  (i.e. Magnetization curve  $OE$ ). The amount of offset “ $FO$ ” is called the retentivity or the remanence or the level of residual magnetism.



# EXPLANATION

---

- As  $H$  is increased to large values in the negative direction,  $B$  reaches saturation but in the opposite direction at point "I". Almost all of the magnetic domains are aligned in opposite direction to that at point E of positive saturation.  $H$  is varied from its maximum negative value to zero. Then  $B$  reaches point "J." This point shows residual magnetism equal to that achieved for positive values of  $H$  ( $OF = OJ$ )

# EXPLANATION

---

- H is increased back from zero to maximum in the positive direction. Then B reaches zero value at “K” i.e. it does not pass through the origin of the graph. OK indicates the amount of field H required to nullify the residual magnetism OJ retained in the opposite direction. H is increased from point “K” further in the positive direction, then again the saturation of B is reached at point “E” and the loop is completed.

# EXPLANATION

---

- ① 1.Retentivity - A measure of the residual flux density corresponding to the saturation of a magnetic material. It is a material's ability to retain a certain amount of residual magnetic field when the magnetizing force is removed after achieving saturation (The value of B at point E on the hysteresis curve).

# EXPLANATION

---

- ② 2. Residual Magnetism or Residual Flux -  
The magnetic flux density  $B$  that remains in a material when the magnetizing field intensity  $H$  is zero. Residual magnetism and retentivity are same only when the material is magnetized to the saturation point. However, it may be lower than the retentivity value otherwise.

# EXPLANATION

---

- ③ 3. Coercive Forc Coercivity It is the amount of reverse magnetizing field intensity which must e or be applied to a magnetic material to make the magnetic flux density of ferromagnetic material return to zero after it has reached saturation. (The value of H at point G on the hysteresis curve).

# EXPLANATION

---

- ④ 4. Reluctance - It is the opposition that a ferromagnetic material shows to the establishment of a magnetic field. Reluctance is analogous to the resistance in an electrical circuit

# EXPLANATION

---

- ⑤ 5. Permeability,  $\mu$ - Permeability is the property of a material that measures the ease with which a magnetic flux is established in it.  $\mu$  is negative in the II and IV quadrants and positive in the I and III quadrants of the B-H graph (i.e. the Hysteresis curve).



---

**THANK YOU**